

SPECIFICATION VICTORIAN FLOOR TILE	
Tested to:	BS EN ISO 14411:2016, in conjunction with BS EN ISO 10545 parts 1-16
Description:	Annex H , dry pressed with low water absorption 0.5% < Eb ≤ 3% Group BIb.
BS EN ISO 10545-2:	Conforms to all standards of dimensions and surface quality.
BS EN ISO10545-2:	Length and width working tolerance: N < 7 cm ± 0.5 mm, 7 cm ≤ N < 15 cm ± 0.9 mm N ≥ 15 cm ± 0.6% max 2.0 mm
MOHS UNE 67-101-92:	Surface Resistance: 7.
BS EN ISO 10545-3:	Water absorption ≤ 3%.
BS EN ISO 10545-4:	Strength S > 1750 N.
BS EN ISO 10545-5:	Coefficient of restitution: conforms to standard
BS EN ISO 10545-6:	Deep abrasion < 175 mm: conforms to standard
BS EN ISO 10545-7:	Surface abrasion for glazed tiles. Wear rating on printed tiles: PEI Class 4
BS EN ISO 10545-9:	Thermal shock resistance: conforms to standard
BS EN ISO10545-12	Frost resistance: 100 freeze thaw cycles: no damage
BS EN ISO 10545-13:	Chemical resistance UA, ULA, UHA.
BS EN ISO 10545-14:	Determination of resistance to stains > 3 Conforms to standard
BS 7976-2:	Pendulum 4S 96 slider [printed]: >63 dry and >49 wet. Pendulum 4S 96 slider [unprinted]: >50 dry and >40 wet
BS 7976-2:	Pendulum TRRL 55 slider [printed]: >90 dry and >35 wet Pendulum TRRL 55 slider [unprinted]: >26 wet
DIN 51097:	Inclined platform test under wet bare foot conditions: A
DIN 51130	Inclined platform test under shod conditions: R10
96/603/ECC	Reaction to Fire: Class A1 <sub>FL</sub>

Aug 2016 Issue 4